

The logo for CRAIG, featuring the word "CRAIG" in a bold, blue, sans-serif font. A blue curved line arches over the letters "A" and "I".

Adhesives and Coatings

ISO 9001-2000 Certified
The Chemistry of Customer Attention

80 Wheeler Point Rd.
Newark NJ, 07105

Phone: (973) 344-1483
Fax: (973) 344-4767
www.craigadhesives.com

Craigcure™ 1034MSD2

Application

High performance UV radiation curing laminating adhesive designed to cure at high press speeds. Applied by roll coaters and flexo equipment. In line corona treatment to 42-48 dynes is suggested for best results. Anilox roll suggestion ranges from 390 to 600 line screen with adequate nip and roll pressure before UV lights.

Some features include: fast cure response, excellent leveling and flow properties, adhesion to a wide variety of inks, films, and paper substrates. Films need to be checked for light transmission as each film absorbs UV light at different rates and will be proportionately detrimental to the cure of this product.

Used on labels, book covers, menu jackets, various indirect food and cosmetic packages, folding cartons, baseball and sports cards, Point-of-Purchase displays and a wide range of printed substrates.

Craigcure™ 1034 MSD2 does not contain any HDODA and is used on labels for plastic water bottles.

Some inks or press varnishes may be incompatible with this laminating adhesive. Please check before running on press.

Caution: *UV coatings may fade rhodamine and reflex blue inks; check for compatibility.*

Physical Properties

APPEARANCE: Optically clear, colorless to amber liquid.

VISCOSITY: 700 - 950 CPS (Brookfield, 20 rpm, #4 spindle, 77°F).

WEIGHT /GALLON(LBS): 9.1 +/- 0.1

SOLIDS: 100.00%

VOC: 0.00%

SHELF LIFE: Six months in closed container.

STORAGE CONDITIONS: Store below 90°F. Keep away from sunlight, artificial light and excessive heat. If very cold, product should be warmed slowly. Low temperatures will thicken product; high temperatures will thin product.

CURE SPEEDS: Will cure tack free under a UV dosage of 100 mj/cm² or more. Actual press speed will depend on the number of lamps, power of lamps and the efficiency of the reflectors.

The information contained herein is to the best of our knowledge true and correct and any suggestions are made without guarantee, express or implied, since the conditions of use are beyond our control. *Craig Adhesives & Coatings* disclaims any liability incurred in connection with the use of these data or suggestions. Nothing contained herein shall be construed as a recommendation to infringe on any existing patents covering any material or its use.